



STYCAST 2651-40 W1

August 2016

PRODUCT DESCRIPTION

LOCTITE STYCAST 2651-40 W1 provides the following product characteristics:

Technology	Epoxy
Appearance (Resin)	Black
Product Benefits	<ul style="list-style-type: none">• Low viscosity• Room temperature cure capability• Can be colour coded to specification
Cure	Room temperature or Heat cure
Application	Potting, Encapsulant

LOCTITE STYCAST 2651-40 W1 epoxy encapsulant is designed for general purpose applications and has excellent adhesion to a wide variety of substrates. When fully cured, the material is readily machined with carbide tools.

LOCTITE STYCAST 2651-40 W 1 can be used with a variety of catalysts. For more information on mixed properties when used with other available catalysts, please contact your local technical service representative for assistance and recommendations.

CATALYST DESCRIPTION

LOCTITE CAT 9 provides the following product characteristics:

Product Benefits	<ul style="list-style-type: none">• General purpose• Good chemical resistance• Good physical strength
Cure	Room temperature cure

LOCTITE CAT 24LV provides the following product characteristics:

Product Benefits	<ul style="list-style-type: none">• Low color• Low viscosity• Excellent thermal shock and impact resistance• Excellent adhesion to Glass
Cure	Room temperature cure

LOCTITE CAT 27-1 provides the following product characteristics:

Product Benefits	<ul style="list-style-type: none">• Long pot life• Excellent chemical resistance• Good physical and chemical properties at elevated temperatures
Cure	Heat cure

TYPICAL UNCURED PROPERTIES

LOCTITE STYCAST 2651-40 W1

Brookfield Viscosity , mPa·s (cP):	
Spindle 6, speed 5 rpm	33,000
Density, g/cm ³	1.5
Shelf Life @ 18 to 25°C (from date of manufacture), days	365
Flash Point - See SDS	

LOCTITE CAT 9

Viscosity @ 25 °C, mPa·s (cP)	450
Density (g/cc ³)	1.0
Flash Point - See SDS	

LOCTITE CAT 24LV

Viscosity @ 25 °C, mPa·s (cP)	15
Density, g/cm ³	1.05
Flash Point - See SDS	

LOCTITE CAT 27-1

Viscosity @ 25 °C, mPa·s (cP)	275
Density, g/cm ³	1.05
Flash Point - See SDS	

TYPICAL UNCURED PROPERTIES AS MIXED

LOCTITE STYCAST 2651-40 W1 with LOCTITE CAT 9

Mix Ratio, Material:Catalyst:	
By Weight	100 : 9
By Volume	100 : 13.5
Work Life, 100 grams, @ 25°C, minutes	45

LOCTITE STYCAST 2651-40 W1 with LOCTITE CAT 24LV

Mix Ratio, Material:Catalyst:	
By Weight	100 : 18
By Volume	100 : 27
Work Life, 100 grams, @ 25°C, minutes	30

LOCTITE STYCAST 2651-40 W1 with LOCTITE CAT 27-1

Mix Ratio, Material:Catalyst:	
By Weight	100 : 15
By Volume	100 : 22
Work Life, 100 grams @ 25°C, hours	2



TYPICAL CURING PERFORMANCE**Cure Schedule****LOCTITE STYCAST 2651-40 W1 with LOCTITE CAT 9**

16 to 24 hours @ 25°C or
4 to 6 hours @ 45°C or
1 to 2 hours @ 65°C

LOCTITE STYCAST 2651-40 W1 with LOCTITE CAT 24LV

24 hours @ 25°C or
4 to 6 hours @ 45°C or
2 to 4 hours @ 120°C

LOCTITE STYCAST 2651-40 W1 with LOCTITE CAT 27-1

4 hours @ 120°C

For optimum performance, follow the initial cure with a post cure of 4 to 6 hours at the highest expected use temperature.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL**LOCTITE STYCAST 2651-40 W1 with LOCTITE CAT 9****Physical Properties**

Hardness, Shore D	90
Glass Transition Temperature, °C:	
TMA	117
DMA, Tangent Delta	110
Coefficient of Thermal Expansion , ppm/°C:	
Below Tg	60
Above Tg	148
Young's modulus (E) :	
@ 35°C	N/mm ² 4,463 (psi) (647,303)
@ 50°C	N/mm ² 4,361 (psi) (632,509)
@ 100°C	N/mm ² 726 (psi) (105,297)
@ 150°C	N/mm ² 101 (psi) (14,648)

Weight Loss , %:

@ 150°C	0.04
@ 200°C	0.1
@ 250°C	0.21
@ 300°C	0.38
@ 700°C	58.6

Thermal Conductivity, W/(m-K)	0.48
Linear Shrinkage, %	0.5
Water Absorption, %:	
After 1 day @ 25 °C	0.03
After 7 days @ 25 °C	0.07
Operating temperature, °C:	
Continuous	-40 to +130
Intermittent	-40 to +150

Electrical Properties

Volume Resistivity, ohm-cm	1.4×10 ¹⁵
Surface Resistivity, ohms	6.6×10 ¹⁵

Dielectric Constant / Dissipation Factor:

@ 50 Hz	4.8/0.052
@ 1 KHz	4.6/0.044
@ 1 MHz	3.9/0.03

LOCTITE STYCAST 2651-40 W1 with LOCTITE CAT 24LV**Physical Properties**

Hardness, Shore D	88
Glass Transition Temperature, °C:	
TMA	73
DMA, Tangent Delta	77
Coefficient of Thermal Expansion , ppm/°C:	
Below Tg	42
Above Tg	167
Young's modulus (E) :	
@ 35°C	N/mm ² 3,540 (psi) (513,433)
@ 50°C	N/mm ² 3,372 (psi) (489,067)
@ 100°C	N/mm ² 50 (psi) (7,251)
@ 150°C	N/mm ² 60 (psi) (8,702)

Weight Loss , %:

@ 150°C	0.2
@ 200°C	0.34
@ 250°C	0.45
@ 300°C	0.57
@ 700°C	58.2
Thermal Conductivity, W/(m-K)	0.46
Linear Shrinkage, %	0.84
Water Absorption:	
After 1 day @ 25 °C	0.05
After 7 days @ 25 °C	0.15
Operating temperature, °C:	
Continuous	-65 to +105
Intermittent	-65 to +120

Electrical Properties

Volume Resistivity, ohm-cm	1.6×10 ¹⁵
Surface Resistivity, ohms	2.2×10 ¹⁵
Dielectric Constant / Dissipation Factor:	
@ 50 Hz	4.9/0.051
@ 1 KHz	5.1/0.044
@ 1 MHz	3.9/0.051

LOCTITE STYCAST 2651-40 W1 with LOCTITE CAT 27-1**Physical Properties**

Hardness, Shore D	94
Glass Transition Temperature, °C:	
TMA	145
DMA, Tangent Delta	141
Coefficient of Thermal Expansion , ppm/°C:	
Below Tg	49
Above Tg	144

Young's modulus (E) :	
@ 35°C	N/mm ² 3,100 (psi) ()
@ 50°C	N/mm ² 3,040 (psi) ()
@ 100°C	N/mm ² 2,600 (psi) ()
@ 150°C	N/mm ² 70 (psi) ()
Weight Loss , %:	
@ 150°C	0.1
@ 200°C	0.2
@ 250°C	0.32
@ 300°C	0.46
@ 700°C	59.8
Thermal Conductivity , W/(m-K)	0.5
Linear Shrinkage, %	0.87
Water Absorption:	
After 1 day @ 25 °C	0.04
After 7 days @ 25°C	0.1
Operating temperature, °C:	
Continuous	-40 to +175
Intermittent	-40 to +200

Electrical Properties

Surface Resistivity, ohms	6.5×10 ¹⁶
Volume Resistivity, ohm-cm	2.8×10 ¹⁵
Dielectric Constant / Dissipation Factor:	
@ 50 Hz	4.8/0.039
@ 1 KHz	4.8/0.04
@ 1 MHz	4.0/0.04

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE

1. Complete cleaning of the components and substrates should be performed to remove contamination such as dust, moisture, salt and oils which can cause electrical failure, poor adhesion or corrosion in an embedded part.
2. Some filler settling is common during shipping and storage. For this reason, it is recommended that the contents of the shipping container be thoroughly mixed prior to use.
3. Power mixing is preferred to ensure a homogeneous product.
4. Accurately weigh resin and hardener into a clean container in the recommended ratio. Weighing apparatus having an accuracy in proportion to the amounts being weighed should be used.
5. Blend components by hand, using a kneading motion, for 2 to 3 minutes. Scrape the bottom and sides of the mixing container frequently to produce a uniform mixture.
6. If possible, power mix for an additional 2 to 3 minutes. Avoid high mixing speeds. This can entrap excessive amounts of air. It can also cause overheating of the mixture, resulting in reduced working life.
7. To ensure a void-free embedment, vacuum deairing should be used to remove any entrapped air introduced during the mixing operation.
8. Vacuum deair mixture at 1 to 5 mm mercury. The foam will rise several times the liquid height and then subside.
9. Continue vacuum deairing until most of the bubbling has ceased. This usually takes 3 to 10 minutes.
10. To facilitate deairing, gentle warming will also help but working life will be shortened. Reduced viscosity provides easy air release upon standing for a few minutes.

11. Pour mixture into cavity or mold.
12. Gentle warming of the mold or assembly reduces the viscosity. This improves the flow of the material into the unit having intricate shapes or tightly packed coils or components.
13. Further vacuum deairing in the mold may be required for critical applications.
14. During storage at room temperature for long periods, it is possible that the viscosity of LOCTITE STYCAST 2651-40 W1 may increase and may exceed its upper specification limit. The viscosity can be brought back to the normal level by moderate mixing.

STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : 18 to 25 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

(°C x 1.8) + 32 = °F
 kV/mm x 25.4 = V/mil
 mm / 25.4 = inches
 N x 0.225 = lb
 N/mm x 5.71 = lb/in
 psi x 145 = N/mm²
 MPa = N/mm²
 N·m x 8.851 = lb·in
 N·m x 0.738 = lb·ft
 N·mm x 0.142 = oz·in
 mPa·s = cP

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other

written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 1

Supplied by: www.hitek-ltd.co.uk +44 (0)1724 851678		HITEK ELECTRONIC MATERIALS LTD
--	---	--

Americas
+1.888.943.6535

Europe
+32.1457.5611

Asia
+86.21.3898.4800

For the most direct access to local sales and technical support visit: www.henkel.com/electronics